

Indoor/Outdoor Tight Buffer Fiber Drop Cable 4.5mm SM G657 1 core Aramid Yarn Single Jacket LSZH-OFNR

v1.0

Shenzhen UnitekFiber Solution Limited

All rights reserved

UnitekFiber Shenzhen UnitekFiber Solution Limited

Catalogue

	1 Cable requirements	. 3
	1.1 Fiber requirements	3
	1.2 General requirements of optical cable	4
	1.3 Cable section view	4
	1.4 Mechanical requirements of optical cable (according to IEC60794-2-50)	5
	1.5 Environment requirements of optical cable (according to IEC60794-2-50 and YD/T1258.2)	6
	1.6 Flammability	7
	1.7 Outer sheath mechanical performance	7
2	Packaging requirement	7
3	Edition record	7

UnitekFiber Shenzhen UnitekFiber Solution Limited

1 Cable requirements

1.1 Fiber requirements

Item	Detail	Requirement
Fiber type	/	G.657A1
	Wavelength	1310nm
Mode field diameter	Range of nominal values	8.6µт -9.8µт
	Tolerance	±0.4 µm
	Nominal	125.0µm
Cladding diameter	Tolerance	±0.7 µm
Core concentricity error	≤0.5µm	
Cladding non-circularity	≤0.7%	
Casting diameter	Nominal	245µm
Coating diameter	Tolerance	±5µm
Coating-cladding concentricity error	≤12.0µm	
Cut-off wavelength	≤1260 nm	

Table 1. Single mode fiber requirements

	Radius(mm)	25	15	10
Uncabled fiber macrobending loss	Number of turns	10	1	1
	Max. at 1550 nm(dB)	0.03	0.1	0.5
	Max. at 1625 nm (dB)	0.1	0.2	1.0
Min. proof stress		0.69 GPa		
Dynamic fatigue parameter		≥20		
	$\lambda_{0\min}$		1300 nm	
Chromatic dispersion coefficient	$\lambda_{0 ext{max}}$	1324 nm		
	S _{0max}	0.09	92 ps/nm^2	× km
Other parameters meet standard ITU-T G.65				



1.2 Cable section view




Figure 1 Optical cable section view

1.3 General requirements of optical cable

Items Fiber Count		Specifications
		1
	Dimension	850±50µm
Tight-buffered Fiber	Material	PVC
	Color	White
	Dimension	4.5±0.1mm
Jacket	Material	LSZH-OFNR
	Color	Black

Table 2. General requirements of optical cable

Mechanical and Environmental Characteristics

Items	Unite	Specifications
Tension(Long Term)	N	200
Tension (Short Term)	N	400
Crush (Long Term)	N/10cm	200
Crush (Short Term)	N/10cm	1000
Min. Bend Radius (Dynamic)	mm	20D
Min. Bend Radius (Static)	mm	10D
Operating Temperature	°C	-20~+60
Storage Temperature	°C	-20~+60



Sheath color	Black
Other perfo	rmances
Min. bending radius of work	20mm
Other parameter meet standar	IEC60794-2-50, YD/T1258.2, ITU-T G.657

Item	Test Method	Requirements
Tensile	Method: IEC 60794-1-2-E1A Diameter of chuck drums and transfer devices: approximately 250mm Rate of transfer device: 100 mm/min or 100N/min Sample length: not less than 50m Load: 100N for 5 min	No change in attenuation at 1550nm, and fiber strain shall be less than 0.4% during the test. Under visual examination without magnification, no damage to the sheath or to the cable elements after test.
Crush	Method: IEC 60794-1-2-E3 Force: 500 N/10cm Duration: 1 min Length between test locations: 500 mm	No change in attenuation at 1550nm after test. Under visual examination without magnification, no damage to the sheath or to the cable elements. The imprint of the striking surface on the sheath is not considered mechanical damage.
Impact	Method: IEC 60794-1-2-E4 Radius of striking surface: 12.5 mm Impact energy: 1.0 J Number of impacts: at least 3, each separated at least 500 mm	No fiber breakage. Under visual examination without magnification, no damage to the sheath or to the cable elements. The imprint of the striking surface on the sheath is not considered mechanical damage.
Repeat bending	Method: IEC 60794-1-2-E6 Bending radius: 30mm Number of cycles: 200 Mass of weights: 2kg	 1.≤0.1dB change in attenuation at 1550nm during the test. 2. There shall be no damage to the cable elements under visual inspection.
Flexing	Method: IEC 60794-1-2-E8 Number of cycles: 300 Pulley diameter: 60mm Mass of weights: 2kg	No fiber breakage. Under visual examination without magnification, no damage to the sheath or to the cable elements
Bending	Method: IEC 60794-1-2-E11A Mandrel diameter: 30mm Tensile: 10N Number of turns per helix: 6	 ≤0.1dB change in attenuation at 1550nm during the test. There shall be no damage to the cable elements under visual inspection.



	Number of cycles: 3	
	Method: IEC 60794-1-2-E7	
	Number of cycles: 10	1. ≤ 0.1 dB change in attenuation at
Τ	Distance between fixed and rotation clamp:	1550nm during the test.
Torsion	250mm	2. There shall be no damage to the cable
	Tension load: 20 N	elements under visual inspection.
	Torsion angle: ±180°	
IZ: 1	Method: IEC 60794-1-2-E10	NT 1' 1 1 11
Kink	Minimum loop diameter: 10mm	No kink shall occur
	Method: IEC60794-2-50 Annex B.	
Sheath pull-off	Rate of separation: ≤ 200 mm/min.	The force to strip the sheath shall not be
force	Strip length: 50 mm.	greater than 15N
	Suip lengui. 50 mm.	greater than 1510

Remark: "No attenuation changes" is considered as the attenuation changes ≤0.05 dB.

1.5 Environment requirements of optical cable (according to IEC60794-2-50 and YD/T1258.2)

Table 4.	Environment	requirements	of a	ontical cable
100000 //				

Item	Test Method	Requirements
Temperature cycling	Method: IEC 60794-1-2-F1 Temperature: -25°C~75°C Sample length: ≥1000m Number of cycles: 2 The cooling and heating rate: 1 °C/min. hold time at every temperature plateau should be 8h.	The variation on attenuation shall be less than 0.5dB/km; There shall be no damage to the cable elements under visual inspection.
Cable bending at high temperature	Method: Huawei requirements Temperature :75°C for 5 hours Bending diameter: 6mm Number of turns per helix: 4	No crack of cable sheath under visual inspection.
Cable bending at low temperature	Method: IEC 60794-1-2-E11A (see IEC 60811-1-4, Clause 8) Bending diameter: 30mm Test temperature:-25°C for 8 hours Number of turns per helix: 10 Number of cycles: 2	No fiber shall break during the test, there shall be no damage to the cable elements under visual inspection.
Sheath shrinkage	Method: IEC 60794-2-50 Annex C. Sample length: 1050mm Exposure temperature: 75°C Exposure duration: 24h per cycle Number of cycles: 4	The average of the sheath shrinkage values shall not exceed 20 mm.
Dual 85 test	Test method: Huawei requirements	There shall be no damage to the optical



	Temperature: 85 °C	cable under visual inspection.
	Relative humidity: 85%	
	Sample length:10m	
	Fiber cable coil diameter:40mm	
	Duration of test: 1000 h	
CE de la retien		The finished cable shall comply with
CE declaration	/	2011/65/EU (RoHS)

1.6 Flammability

Table 5. Flame resistant index for OFNR cable

No	Item	Unit	Technology index
1	Flame propagation test	/	IEC 60332-1

1.7 Outer sheath mechanical performance

Outer sheath mechanical performance of indoor optical cable should meet the requirements of table 12.

Table 6. Outer sheath mechanism performance

Item	Requirements			
Outer-sheath material	LSZH(OFNR)			
Un-aged mechanical performance				
Tensile strength, MPa	≥10			
Elongation,%	≥125			
Aging (100°C, 240H) mechanical performance				
After tensile strength variation absolute value,%	≤20			
Elongation,%	≥100			
Aging elongation variation absolute value,%	≤20			

2 Packaging requirement

Packaging materials need to meet environmental protection requirements, and at the same time, during handling and transportation, the packaging needs to have good protection for the product so as not to damage the **product.**

3 Edition record

Date	Author	Reviewer	Version	Revision declaration
2022-1-29	赵朋		V1.0	Final version

End of Document